

Polyester film is tougher and more durable than polycarbonate and PVC film. It offers enhanced chemical resistance and dramatically improved flex life. The Autotex range of textured polyester films extends the functionality of polyester film into areas demanding high abrasion resistance together with excellent receptivity to graphic inks and windowing lacquers. Autotex has been developed for applications requiring a combination of high abrasion resistance and flexibility, such as embossed membrane switches.

PRODUCT DESCRIPTION

Autotex is a high quality textured polyester film, consisting of a base polyester and a flexible chemically bonded, UV-cured textured coating. It is available in sheets and rolls.

Product range:

Autotex Fine	F150, F200, F280
Fine texture	150,200, 280 micron
Autotex Velvet	V150, V200, V280
Velvet texture	150, 200, 280 micron

Primer:

Autotex has an ink adhesion primer on the second surface. This primer confers excellent adhesion to a wide range of solvent based graphic inks. The primer is not recommended for use with UV-cured graphic inks or a combination of solvent and UV graphic inks because the adhesion performance will be inconsistent. A special primer is available for use with UV inks, please see Autotex (7 Series) Product Data Sheet.

Windows:

Autotex can be screen printed with Windotex to obtain a clear window (see Windotex product data sheet). Autotex Fine, because of its lighter texture, will produce clearer windows than Autotex Velvet.

Outdoor use:

In common with most other plastics, Autotex has limited long term resistance to UV light and therefore is not recommended for long term use outdoors. In order to overcome this issue, MacDermid Autotype has specially developed Autotex XE, a UV resistant version of Autotex. Please see Autotex XE Product Data Sheet.

PRODUCT APPLICATIONS

Autotex is used as a substrate in the following applications:

- Membrane switch overlays
- Fascia panels
- Nameplates
- Labels/Product marking



Major benefits

- Long flex life
- Chemical and household cleaner resistance, even at the edges
- Clear window facility
- Embossable
- Excellent scratch resistance
- Consistent low gloss, textured surface
- Attractive appearance

CHEMICAL PROPERTIES

Property	Autotex	Test Method
Chemical Resistance	Resistant to: Alcohols Dilute Acids Dilute Alkalis Esters Hydrocarbons Ketones Household Cleaning Agents*	DIN 42 115
Coefficient of hygroscopic expansion ¹	MD 8×10^{-6} (per 1% RH) TD 7×10^{-6} (per 1% RH)	DuPont Teijin Films Method ¹ Between 40-80% RH
Moisture vapour transmission rate (MVTR) ¹	3.57g/m ² /24 hours	ASTM F372-73
Oxygen transmission rate ¹	8.2ml /m ² /24 hours	ASTM D1434-82 @ 25°C, 77% RH

¹ Data derived from DuPont Teijin Films literature for 125µ Melinex OD.

² The Autotex coating slightly enhances most properties.

* For more detailed information refer to Autotex solvent resistance sheet.

ELECTRICAL PROPERTIES

Property	Autotex	Test Method
Dielectric strength ¹	13.5 kV	ASTM D149-81 6.35mm electrodes in dry air @ 25°C
Dissipation factor ¹	0.005	ASTM D150-70
Surface resistivity	$>10^{13} \Omega/\text{sq}$ 500Vd.c	ASTM D257-83 @ 20°C/54% RH
Volume resistivity ¹	$10^{15} \Omega\text{m}$ 100Vd.c	ASTM D257-83 @ 25°C/1000s

¹ Data derived from DuPont Teijin Films literature for 125µ Melinex OD.

The Autotex coating slightly enhances most properties.



MECHANICAL PROPERTIES

Property	Autotex	Test Method
Young's modulus ¹	3700N/mm ²	ASTM D882
Elongation at break ¹	70%	ASTM D1505
Switch life	>5 million flexes	MacDermid Autotype Method ²
Tensile strength at break ¹	150N/mm ²	ASTM D882
Tensile strength at yield point ¹	100N/mm ²	ASTM D882
Tear strength ¹	350N/mm ²	ASTM D882

¹ Data derived from DuPont Teijin Films literature for 125µ Melinex OD.

² Adapted to MacDermid Autotype Method, see Test method manual.

OPTICAL PROPERTIES

Property	Autotex	Test Method
Gardner Haze Fine Velvet	58% ±5% 71% ±5%	ASTM D1003-77 ¹
Gloss Level (60°) Fine Velvet	7% ±1.5% 4.5% ±1%	ASTM D2457-03 ¹
Texture profile Ra Fine Velvet Rtm Fine Velvet	 1.6µ ±0.2µm 3.1µ ±0.2µm 8µ ±2µm 15.4µ ±2µm	MacDermid Autotype Method ²
Total luminous transmission	92% ±2%	ASTM D1003-77 ¹
UV absorption	1.3 - 1.4	MacDermid Autotype Method ² (370nm)
Yellowness index ²	<3	ASTM E313

¹ Adapted to MacDermid Autotype Method, see Test Method Manual.

² See Test Method Manual

PHYSICAL PROPERTIES

Property	Autotex	Test Method
Density ¹	1.39 g/cm ³	ASTM D1505
Thicknesses F150 F200 F280 V150 V200 V280	 150µ ±10% 200µ ±10% 280µ ±10% 150µ ±10% 200µ ±10% 280µ ±10%	MacDermid Autotype Method ²

¹ Data derived from DuPont Teijin Films literature for 125µ Melinex OD.

² See Test Method Manual



THERMAL PROPERTIES

Property	Autotex	Test Method
Coefficient of thermal expansion ¹	0.002%/degree	DuPont Teijin Films Method
Coefficient of humidity expansion ¹	0.009%/RH	DuPont Teijin Films Method
Dimensional stability	0.2% maximum shrinkage MD at 120°C	MacDermid Autotype Method ²
Maximum processing temperature	120°C	
Maximum use temperature	Low humidity (<10%RH) 85°C High humidity (10-95%RH) <60°C	
Minimum use temperature	-40°C (-40F)	MacDermid Autotype Method ²

¹ Data derived from DuPont Teijin Films literature for 125µ Melinex OD

² See Test Method Manual

OZONE DEPLETING SUBSTANCES

EC Regulation 594/91 classifies ozone depleting substances into a number of different groups, I-VI. Autotex does NOT contain any substance classified in groups I-VI nor have any of the substances been used by MacDermid Autotype during manufacture. For details of the content of each of the groups, please see separate ozone depleting substances document.

Revision 10/09/V1

The information and recommendations in this publication are believed to be accurate and are offered in good faith but do not constitute specifications. Suggestions concerning uses and applications are only the opinion of MacDermid Autotype Limited and users should carry out their own testing procedures to confirm suitability for their purposes. Except in the case of death or personal injury caused by the materials, MacDermid Autotype Limited MAKES NO WARRANTY OF ANY KIND AND EXCLUDES ANY STATUTORY WARRANTY EXPRESS OR IMPLIED other than that materials conform to their current applicable standard specification. Statements herein therefore should not be construed as guarantees of satisfactory quality or fitness for purpose. The responsibility of MacDermid Autotype Limited for claims arising out of breach of guarantee, negligence, strict liability or otherwise is limited to the purchase price of the material. Suggestions concerning working practices and procedures are based on the practices adopted by existing users of the products and are made in good faith. IT IS THE RESPONSIBILITY OF THE USER TO ENSURE THAT ALL RELEVANT HEALTH AND SAFETY LAWS AND REGULATIONS ARE COMPLIED WITH. MacDermid Autotype Limited does not provide any advice on such laws and regulations and accepts no responsibility, express or implied, for breach of such regulations. Statements concerning the use of products described herein should not be construed as recommending the infringement of any patent and no liability for infringement arising out of such use is assumed.

