

Autotex S

Product Data Sheet

Autotex Steel (S) is the new finish in the Autotex film range. Autotex S is a textured hardcoat that when printed with a specialist mirror ink creates a stainless steel look.

The introduction of Autotex S allows screen printers to produce a range of products that re-create the effect of stainless steel but with all the benefits you have come to expect with Autotex films. These include high abrasion, solvent and chemical resistance, a film flexible enough to be embossed and withstand >5 million actuations. Autotex S is also receptive to a wide range of graphic and windowing inks allowing creative designers the opportunity to produce unique graphics and designs.

PRODUCT DESCRIPTION

Autotex S is a high quality textured film, consisting of a polyester base coated with a flexible chemically bonded, UV-cured textured coating.

Product range:

Autotex Steel	S150	150 micron	Solvent inks
	S200	200 micron	Solvent inks
	S157	150 micron	Solvent and UV inks
	S207	200 micron	Solvent and UV inks

Primer:

Autotex S has an ink adhesion primer on the second surface. This primer confers excellent adhesion to a wide range of graphic inks.

Windows:

Autotex S can be windowed using Windotex to improve the clarity of incorporated LED and LCD windows. For optimum printing recommendations please refer to the specific Autotex S section on the Windotex product data sheet.

Formats:

Autotex S is available in sheet and roll format. The maximum roll size is 122cm x 400m with the grain running in the Machine Direction along the roll length. Standard size sheets are 61cm x 91.5cm with the grain running along the 91.5cm length.

PRODUCT APPLICATIONS

Autotex S is used as a substrate in the following applications:

- Membrane switch overlays
- White goods appliances (to create a stainless steel finish)
- Mobile phone fascias
- Nameplates
- Labels/Product marking
- Fascia panels



Major Benefits

- Consistent low gloss, textured surface that when printed with silver mirror inks gives an excellent replication of stainless steel
- Impact resistant unlike stainless steel
- No fingerprinting unlike stainless steel
- Can incorporate secret till lit features unlike stainless steel
- Second surface printing of text that is clearly viewable through the hardcoat surface
- Embossable with a long flex life
- Chemical and household cleaner resistance even at the edges
- Clear window facility
- Excellent scratch resistance

CHEMICAL PROPERTIES

Property	Autotex S	Test Method
Chemical Resistance	Resistant to: Alcohols Dilute acids Dilute alkalis Esters Hydrocarbons Ketones Household cleaning agents*	DIN 42 115
Coefficient of hygroscopic expansion ¹	MD 8×10^{-6} (per 1% RH) TD 7×10^{-6} (per 1% RH)	DuPont Teijin Films Method ¹ Between 40-80% RH
Moisture vapour transmission rate (MVTR) ¹	3.57g/m ² /24 hours	ASTM F372
Oxygen transmission rate ¹	8.2ml/m ² /24 hours	ASTM D1434 @ 25 °C, 77% RH

¹ Typical data derived from DuPont Teijin Films

² The Autotex coating slightly enhances most properties

* For more detailed information refer to Autotex resistance sheet.

ELECTRICAL PROPERTIES

Property	Autotex S	Test Method
Dielectric strength ¹	13.5 kV	ASTM D149 6.35mm electrodes in dry air @ 25 °C
Dissipation factor	0.005	ASTM D150
Surface resistivity ¹	$>10^{13} \Omega / \text{sq } 500\text{Vd.c}$	ASTM D257 @ 20 °C / 54% RH

¹ Data derived from DuPont Teijin Films.



MECHANICAL PROPERTIES

Property	Autotex S	Test Method
Young's modulus ¹	3700N/mm ²	ASTM D882
Elongation at break ¹	70%	ASTM D1505
Switch life	>5 million flexes	MacDermid Autotype Method ²
Tensile strength at break ¹	150N/mm ²	ASTM D882
Tensile strength at yield point ¹	100N/mm ²	ASTM D882
Tear strength ¹	350N/mm ²	ASTM D882

¹Data derived from DuPont Teijin Films.

²See Test Method Manual

OPTICAL PROPERTIES

Property	Autotex S	Test Method
Gardner Haze	50% ±5%	ASTN D1003 ¹
Gloss Level (60°) With the grain (MD) Against the grain (TD)	25-30% 8-10%	ASTM D2457-03 ¹
Texture profile Ra with the grain (MD) Ra against the grain (TD) Rz with the grain (MD) Rz against the grain (TD)	0.3-0.7µm 0.9-1.5µm 2.0-3.0µm 6.5-8.5µm	MacDermid Autotype Method ²
Total Luminous Transmission	90% ± 2%	ASTM D1003 ¹
Yellowness index ²	<3	ASTM E313

¹Adapted to MacDermid Autotype method, see Test Method Manual

²See Test Method Manual

PHYSICAL PROPERTIES

Property	Autotex S	Test Method
Relative density ¹	1.39g/cm ³	ASTM D1505
Thickness S150/S157 S200/S207	150µ ± 10% 200µ ±10%	MacDermid Autotype Method ²

¹Data derived from DuPont Teijin Films

²See Test Method Manual



THERMAL PROPERTIES

Property	Autotex S	Test Method
Coefficient of thermal expansion ¹	0.002%/degree	DuPont Teijin Films Method ¹
Coefficient of humidity expansion ¹	0.0009%/RH	DuPont Teijin Films Method ¹
Dimensional stability	0.2% max. shrinkage MD @ 120 °C	MacDermid Autotype Method ²
Maximum processing temperature	120 °C	
Maximum use temperature	Low humidity (<10%RH) 85 °C High humidity (10-95%RH) ≤60 °C	
Minimum use temperature	-40 °C (-40F)	MacDermid Autotype Method ²

¹Data derived from DuPont Teijin Films

² See Test Method Manual

RECOMMENDED INKS

Manufacturer	Ink Range
COATES	Touchkey HG
DUBUIT	24800
JUJO	9000 series 9100 series
NAZDAR	8800 series GV
MARABU	Marastar SR Maraswitch MSW
PRINTCOLOR	Series 388 Easy Switch 346
PROELL	Thermojet + 5020 adhesion improver M1 (Mirror ink*) M2 (Mirror ink)
SERICOL	Seritec TH Polyplast PY Techmark
SEIKO	PAL GAP Advance GAT series
TEIKOKU	EG IPX series
TOYO	SS66-000
VISPROX	Multiplast 300



OZONE DEPLETING SUBSTANCES

EC Regulation 594/91 classifies ozone depleting substances into a number of different groups, I-VI. Autotype products do NOT contain any substance classified in groups I-VI nor have any of the substances been used by MacDermid Autotype during manufacture. For details of the content of each of the groups, please see separate ozone depleting substances document

ENVIRONMENTAL & DISPOSAL

EU Directives 2003/11/EC; 2002/95/EC; 2002/525/EC; 2006/122/EC (ROHS)

Restriction on use of Pentabromodiphenyl ether CAS 32534-81-9
Octabromodiphenyl ether CAS 32536-52-0
Polybrominated biphenyls
Polybrominated diphenylether
Lead, Mercury, Cadmium, Chromium VI
Perfluorooctanesulphonate, Perfluorooctanic acid & related compounds

In relation to the above directive, Autotype products do not contain polybrominated biphenyl & diphenyl ethers, brominated compounds, perfluorooctane derivatives or any flame retardant agents. Autotype products are also free of the heavy metals specified in the above Directives (lead, mercury, cadmium, chromium VI).

EU Directive 2002/96/EC (WEEE) relates to the Disposal and Recycling of Waste Electronic and Electrical Equipment. Autotype films are compliant with this directive and do not contain any materials identified in Directives 2003/11/EC & 2002/53/EC (also 2037/2000). MacDermid Autotype Limited have no responsibility for the compliance of finished equipment, which will contain materials from other suppliers.

This range of products comprises films with a chemically treated surface which renders them difficult to recycle in appropriate material recovery schemes. The product contains no substances listed on the EC Black or Grey lists and may be safely disposed of in a landfill or by authorized incineration.

Revision 02/10/V3

The information and recommendations in this publication are believed to be accurate and are offered in good faith but do not constitute specifications. Suggestions concerning uses and applications are only the opinion of MacDermid Autotype Limited and users should carry out their own testing procedures to confirm suitability for their purposes. Except in the case of death or personal injury caused by the materials, MacDermid Autotype Limited MAKES NO WARRANTY OF ANY KIND AND EXCLUDES ANY STATUTORY WARRANTY EXPRESS OR IMPLIED other than that materials conform to their current applicable standard specification. Statements herein therefore should not be construed as guarantees of satisfactory quality or fitness for purpose. The responsibility of MacDermid Autotype Limited for claims arising out of breach of guarantee, negligence, strict liability or otherwise is limited to the purchase price of the material. Suggestions concerning working practices and procedures are based on the practices adopted by existing users of the products and are made in good faith. IT IS THE RESPONSIBILITY OF THE USER TO ENSURE THAT ALL RELEVANT HEALTH AND SAFETY LAWS AND REGULATIONS ARE COMPLIED WITH. MacDermid Autotype Limited does not provide any advice on such laws and regulations and accepts no responsibility, express or implied, for breach of such regulations. Statements concerning the use of products described herein should not be construed as recommending the infringement of any patent and no liability for infringement arising out of such use is assumed.

